



AquaPro Enamel Primer 113 series

“AquaPro Enamel Primer 113 Series” designed for AquaPro Enamel Paint 112 line. This is suitable for all metal and wood surfaces, showing excellent adhesion to the substrates that reinforces the capability of topcoat. It is jet dry, easy application and contains low VOC content.

Usage	For primer purpose, this product can reinforce the capability of topcoat. It is suitable for all metal and wood surfaces.
Finish	Semi Gloss
Color	White
Packing	4 Liter, 18 Liters
Advantages	<ul style="list-style-type: none"> ✓ Jet dry ✓ Excellent adhesion ✓ Low VOC ✓ Ease of application
Base Resin	Synthetic latex
Drying Time	
– Touch Dry	1 hour
– Hard Dry	2 hours
– Overcoating	Minimum 4 hours
Coverage	Around 11m ² /ltr. @30 microns dry film thickness per coat Actual coverage depends on surface conditions and also application conditions.
Shelf Life	18 months
Application Method	Ready-to-use after thinning with clear water and stirring thoroughly.
Recommended No. of coat	1 coats
Thinning Ratio	
– Brush/Roller	Dilute 10 parts of the paint with around 2.5 to 3.5 parts of clear water (25-35%)
Application	<ol style="list-style-type: none"> 1. Surfaces to be coated must be sound, clean, free from dust, rust, oil, grease, moisture and foreign matters. For recoating old surfaces, all chalked and scaled materials must be removed before painting. 2. Stir the paint well before use. 3. If the mixture thickens or spoils, do not thin. Properly throw it away. Mix fresh materials again for new paint.

Technical Bulletin No.: 113/190618

葉氏駱駝(香港)有限公司 YIP'S CAMEL (HONG KONG) LIMITED

香港灣仔告士打道77-79號富通大廈27樓

27/F., Fortis Tower, 77-79 Gloucester Road, Wanchai, Hong Kong

電話 Tel: (852) 2675 2333

傳真 Fax: (852) 2675 2332

電郵 Email: info@camel.com.hk

網址 Website: <http://www.camel.com.hk>



Conditions

- Maintain temperature in areas to receive coatings at minimum 10°C during application and until coatings have cured.
- Avoid applying the product when relative humidity above 85%.
- Adequately ventilate areas where coatings are being applied. Maintain a reasonably dust-free atmosphere for duration of work.
- Protect adjacent surfaces not scheduled to receive coatings from damage and overcoat.
- Post "Wet Coating" signs while work is in progress and while coatings are curing.
- Material to be delivered and stored in undamaged, original manufacturers' containers.
- Keep container closed when not in use
- Store at cool, dry place. Store above freezing point.

Health & Safety Precautions

- *Ingestion*
- *Eye contact*
- *Skin contact*
- *Inhalation*

Send the affected person to hospital or obtain medical attention immediately. Do not induce vomiting.
 Flush immediately with water and get medical care.
 Flush immediately with water and remove contaminated clothing.
 If irritation persists, refer for medical attention.
 Remove the affected person to fresh air and obtain medical attention if rapid recovery does not occur.

Type of Regulated Paint under the Air Pollution Control (Volatile Organic Compounds) Regulation of Hong Kong: Primers, Sealers and Undercoaters P10-11

VOC content (ready to use): Not exceeding 200gm/Liter

NOTES

- Product data is based on in-house testing methods modified from BS3900/ASTM.
- Content will be updated without prior notice.
- Surface preparation, application method and condition, etc. may affect product performance. We are not responsible for the performance, unless agreed in writing by us.

Technical Bulletin No.: 113/190618

葉氏駱駝(香港)有限公司 YIP'S CAMEL (HONG KONG) LIMITED

香港灣仔告士打道77-79號富通大廈27樓

27/F., Fortis Tower, 77-79 Gloucester Road, Wanchai, Hong Kong

電話 Tel: (852) 2675 2333

傳真 Fax: (852) 2675 2332

電郵 Email: info@camel.com.hk

網址 Website: <http://www.camel.com.hk>