



AQUAPRO ENAMEL PAINT 112 SERIES

"AquaPro Enamel Paint 112 series" is a high quality, multipurpose coating for a variety of interior and exterior applications on all metal surfaces. It is jet dry, easy application and contains low VOC content. The dry film provides very good adaptability to environmental changes, and displays high

gloss and attractive film build which come along with excellent gloss retention and durability.

Usage	Suitable for all metal surfaces		
Finish	High Gloss & Low Gloss		
Color	Standard Colors, 1,050+ computerized tinting colors & tailor-made		
	colors on req		
Packing	High Gloss - 1 Liter, 4 Liters & 18 Liters		
	Low Gloss - 1 Liter, 3 Liters		
Advantages	√ Jet dry		
	√ High gloss & Low Gloss		
	∨ Good gloss retention		
	√ Low VOC		
	√ Ease of application		
	V No chalking, cracking & very slight color fading observed after		
	500 hours in UV/ Condensation Screening Device (actual result		
	varies with colour).		
Base Resin	Synthetic Latex		
Drying Time			
- Touch Dry	1 hour		
- Hard Dry	2 hours		
- Overcoating	Minimum 4 hours		
Coverage	Around 12m ² /ltr. @25 microns dry film thickness per coat		
	Actual coverage depends on surface conditions and also application		
Shelf Life	conditions.		
Recommended Primer	36 months		
Recommended Frimer	AquaPro Matting Agent 110 This matting agent is specially formulated for lowering the gloss level of water based paint. Desired gloss level of paint such as Semi Gloss and Matt can be easily achieved. It is suitable for all AquaPro product series.		
Recommended Coating System	Galvanized	Primer	Water-borne GI Primer AR033
3 7	steel (G.I.)	Topcoat	AquaPro Enamel Paint 112
		Primer	AquaPro Rust-Proof Metal Primer 103
	Metal	Undercoat	AquaPro Brushing Enamel Primer 113
		Topcoat	AquaPro Enamel Paint 112
	Wood	Undercoat	AquaPro Brushing Enamel Primer 113
		Topcoat	AquaPro Enamel Paint 112
Application Method	Ready-to-use after thinning with clear water and stirring thoroughly		
Recommended No. of coat	2 coats		

Technical Bulletin No.: 112/241218



電郵 Email: info@camel.com.hk 網址 Website: http://www.camel.com.hk



Thinning Ratio			
- Brush/Roller	Dilute 10 parts of the paint with around 1 to 2 parts of clear		
,	water (10-20%)		
Application	Painting is recommended to carry out on fine day.		
**	2. Surfaces to be coated must be sound, clean, free from dust, rust,		
	oil, grease, moisture and foreign matters. For recoating old		
	surfaces, all chalked and scaled materials must be removed		
	before painting.		
	3. Stir the paint well before use.		
Conditions	 Maintain temperature in areas to receive coatings at minimum 		
	10°C during application and until coatings have cured.		
	 Avoid applying the product when relative humidity above 		
	85%.		
	- Adequately ventilate areas where coatings are being applied.		
	Maintain a reasonably dust-free atmosphere for duration of		
	work.		
	 Protect adjacent surfaces not scheduled to receive coatings from 		
	damage and overcoat.Post "Wet Coating" signs while work is in progress and while		
	coatings are curing.		
	- Material to be delivered and stored in undamaged, original		
	manufacturers' containers.		
	- Keep container closed when not in use		
Health & Cafaty Duagastians	- Store at cool, dry place. Store above freezing point.		
Health & Safety Precautions - Ingestion	Send the affected person to hospital or obtain medical attention		
- ingestion	immediately. Do not induce vomiting.		
- Eye contact	Flush immediately with water and get medical care.		
- Skin contact	Flush immediately with water and get medical care. Flush immediately with water and remove contaminated clothing.		
Skii contact	If irritation persists, refer for medical attention.		
- Inhalation	Remove the affected person to fresh air and obtain medical		
	attention if rapid recovery does not occur.		
	and the state of t		

Type of Regulated Paint under the Air Pollution Control (Volatile Organic Compounds) Regulation of Hong Kong: Rust Preventative Coatings P10-14

VOC content (ready to use): Not exceeding 350gm/Liter

NOTES

- Product data is based on in-house testing methods modified from BS3900/ASTM.
- Content will be updated without prior notice.
- Surface preparation, application method and condition, etc. may affect product performance. We are not responsible for the performance, unless agreed in writing by us.

Technical Bulletin No.: 112/241218



電郵 Email: info@camel.com.hk 網址 Website: http://www.camel.com.hk